



Ürün Özellikleri



		Plank	Herringbone	Chevron
Ağaç Türü	-	Meşe / Ceviz	Meşe / Ceviz	Meşe / Ceviz
Katman Sayısı	-	2 Katmanlı yapı	2 Katmanlı yapı	2 Katmanlı yapı
Bağlantı Sistemi	-	Zıvana ve geçme	Zıvana ve geçme	Zıvana ve geçme
Yüzey Yapısı	-	Fırçalı	Fırçalı	Fırçalı
Pah	-	4	4	4
Papel kalınlığı	mm	4 mm	4 mm	4 mm
Kullanım klasmanı	EN 10874 XP B 53-669	23 *	23 *	23 *
Konut Kullanım Ömrü	-	30 Yıl	30 Yıl	30 Yıl
Toplam kalınlık	mm	13,5 mm.	13,5 mm.	13,5 mm.
Toplam ağırlık	kg/m ²	11 kg.	11 kg.	11 kg.
Ebat	mm	180 x 500 - 2310	110x595	110x515
Paket içeriği	-	6 Plaka	12 Plaka	12 Plaka
Palet içeriği	-	48 Paket	48 Paket	48 Paket
Paket metraj	m ²	2,495	0,785	0,68

*konut yoğun trafik

test sonuçları

Yüzey işleme	-	Ticari yüksek performanslı vernik
Yerden ısıtma ile uyumluluk	-	Uygun (maxi 90 W/m ²) ve düşük sıcaklıkta sıcak su
Isı direnci	m ² K/W	Maks. 0.10
Yangına dayanıklılık	EN 13 501 - 1 (oak)	Dfl - s1
Formaldehit emisyonları	EN 717-1	E1 ≤ 0,124mg/m ³
Çevre programı	Sertifikasyon	PEFC 10-31-1047
Isıl iletkenlik (EN14342)	-	0.14 W /mK

Product Specifications



		Plank	Herringbone	Chevron
Wood Species	-	Oak / Walnut	Oak / Walnut	Oak / Walnut
Number of Layers	-	2-layer structure	2-layer structure	2-layer structure
Joint System	-	Tongue & Groove	Tongue & Groove	Tongue & Groove
Surface Finish	-	Brushed	Brushed	Brushed
Bevel	-	4	4	4
Oak facing thickness	mm	4 mm	4 mm	4 mm
Class of used	EN 10874 XP B 53-669	23 *	23 *	23 *
Residential Lifespan	-	30 Years	30 Years	30 Years
Total Thickness	mm	13,5 mm	13,5 mm	13,5 mm
Total Weight	kg/m²	11 kg.	11 kg.	11 kg.
Dimensions	mm	180 x 500 - 2310	110x595	110x515
Pack content	-	6 Planks	12 Planks	12 Planks
Packs per Pallet	-	48 Packs	48 Packs	48 Packs
Palette content	m²	2,495	0,785	0,68

*domestic high

test results

Surface treatment	-	Commercial high performance varnish
Compatibility with underfloor heating	-	PRE compatible (maxi 90 W/m2) and low temperature hot water
Thermal resistance	m² K/W	Max. 0.10
Fire resistance	EN 13 501 - 1 (oak)	Dfl - s1
Formaldehyde emissions	EN 717-1	E1 ≤ 0,124mg/m³
Envrionmental programme	Certification	PEFC 10-31-1047
Thermal Conductivity	EN14342	0.14 W /mK