

Product description

	Unit	
• Parquet		3 strip
• V-Groove (GO2)		No
• Format (L x w x h)	mm	1180 x 210 x 13
• Facing thickness genuine hardwood	mm	2,5
• Core layer	mm	HDF thickness 9
• Backing layer	mm	Softwood veneer 1,5
• Total thickness	mm	13
• Weight	kg/m ²	10
• Moisture content (when delivered)	%	7-10
• Species offered		Oak
• Surface treatment		Masterresist Lacquer, Oiled or Natural-Oil
• Packaging		Protective edge with recycled carton (95% recycled paper) Climate protection of PE film
• Packaging contents	pack Pallet	8 planks = 1,98m ² 50 packs = 99,12m ²
• Environnemental prog.		15 years domestic use (see conditions on berryalloc.com)
• Warranty		Lifetime for locking system
• Installation		Mechanical loc: Bestloc and BestLoc X-TREME no glue, no tools (see the installation instructions available on berryalloc.com) Floating laying (french installation rule) Glued fitting (french installation rule)
• Underfloor heating	DTU 51.11 DTU 51.2	Suitable (see the specific requirements for wood floors above underfloor heating on berryalloc.com)

Classification	Norm	Unit	Measurements
• Abrasion resistance	CS10 (NF Parquet) EN 13329 (Test S42)	Tour (TT) Tour (TT) Gloss 60°	6000-9000 >700 7 +/- 2 (matt)
• Gloss value			
• Fire class	EN 13 501-1	Oak	Dfl-S1
• Slippery	XP CEN TS 15676	SRT Longitudinal (CV %) SRT Transversal (CV %)	70,5 % (18,8 %) (lacquered) 79,2 % (12,8 %) (lacquered)
• Adhesion	ISO 2409	Adhesion	1
• Thermal resistance		coefficient m ² K/W	Oak : 0,06622
• European class (based on unfinished wood)	EN 685	Oak	23
• Loc System Joint strength		Kg/m Kg/m	Long side > 550 Short side > 1 000
• Marquage CE	EN 14342		
• Formaldehyde emission	EN 717-1	µg/m ³	E1
• VOC emission	ISO 16 000-9	µg/m ³	A+

Maintenance

See instructions on berryalloc.com

For commercial use, please take contact with us.

