

Product description	Unit							
<ul style="list-style-type: none"> • Parquet • V-Groove • Format (L x w x h) 	mm	Single plank on the long sides 1180 x 164 x 14 1980 x 164 x 14						
<ul style="list-style-type: none"> • Facing thickness genuine hardwood 	mm	3,3						
<ul style="list-style-type: none"> • Total thickness 	mm	14						
<ul style="list-style-type: none"> • Weight 	kg/m ²	11						
<ul style="list-style-type: none"> • Moisture content (when delivered) 	%	7-10						
<ul style="list-style-type: none"> • Core layer 	mm	Brown HDF thickness 9,2						
<ul style="list-style-type: none"> • Backing layer 	mm	Softwood veneer 1,5						
<ul style="list-style-type: none"> • Species offered 		Oak						
<ul style="list-style-type: none"> • Surface treatment 		High Performance Ultimtec Soft Touch Lacquer or oiled finish						
<ul style="list-style-type: none"> • Packaging 		Protective edge with recycled carton (95% recycled paper) Climate protection of PE film						
<ul style="list-style-type: none"> • Packaging contents 	pack pallet	<table border="0"> <tr> <td>L 1180 mm</td> <td>L 1980 mm</td> </tr> <tr> <td>8 planks = 1,5481m²</td> <td>6 planks = 1,9482 m²</td> </tr> <tr> <td>66 packs = 102,17m²</td> <td>50 packs = 97,41m²</td> </tr> </table>	L 1180 mm	L 1980 mm	8 planks = 1,5481m ²	6 planks = 1,9482 m ²	66 packs = 102,17m ²	50 packs = 97,41m ²
L 1180 mm	L 1980 mm							
8 planks = 1,5481m ²	6 planks = 1,9482 m ²							
66 packs = 102,17m ²	50 packs = 97,41m ²							
<ul style="list-style-type: none"> • Environnemental prog. • Warranty 		PEFC for Oak, Beech 30 years domestic use - Lifetime for locking system Mechanical loc: Bestloc and BestLoc X-TREME						
<ul style="list-style-type: none"> • Installation 		no glue, no tools (see the installation instructions available on berryalloc.com)						
<ul style="list-style-type: none"> • Underfloor heating 	DTU 51.11 DTU 51.2	Floating laying (french installation rule) Glued fitting (french installation rule) suitable except species beech, maple and jatoba (see the specific requirements for wood floors above underfloor heating on berryalloc.com)						

Classification	Norme	Unit	Mesures
<ul style="list-style-type: none"> • Abrasion resistance 	CS10 (NF Parquet) EN 13329 (Test S42)	Tour (TT) Tour (TT)	15600 (lacquered) >500 (lacquered)
<ul style="list-style-type: none"> • Gloss value 		Gloss 60° Gloss 60° Gloss 60°	27 +/- 2 (satin) 15 +/- 2 (patina) 7 +/- 2 (matt)
<ul style="list-style-type: none"> • Fire class 	EN 13 501-1	Oak, Sapelli, Doussie Merbau, Beech	Dfi-S1 Cfi-S1
<ul style="list-style-type: none"> • Slippery 	XP CEN TS 15676	Longitudinal SRT (CV %) Transversal SRT (CV %)	70,5% (18,8%) 79,2% (12,8%)
<ul style="list-style-type: none"> • Adhésion • Thermal resistance 	ISO 2409	Adhesion coefficient m ² K/W	0 Oak: 0,080 (other species from 0,075 to 0,088)
<ul style="list-style-type: none"> • European class (based on unfinished wood) 	EN 685		
<ul style="list-style-type: none"> • Loc System Joint strength 		Oak / Beech / Doussie Merbau Kg / m	31 33 Long side > 550 Short side > 1.000
<ul style="list-style-type: none"> • Marquage CE • Formaldehyde emission • VOC emission 	EN 14342 EN 717-1 ISO 16 000-9	Kg / m µg/m ³ µg/m ³	E1 E1 A+

Maintenance

See instructions on berryalloc.com

For commercial use, please take contact with us.

