

Product description

	Unit	
<ul style="list-style-type: none"> Parquet V-Groove Format (L x w x h) Facing thickness genuine hardwood Total thickness Weight Moisture content (when delivered) Core layer Backing layer Species offered Surface treatment Packaging 	mm	Single plank on the long sides 1180 x 130 x 11
	mm	2,5
	mm	11
	kg/m ²	9
	%	7-10
	mm	Brown HDF thickness 7,2
	mm	Softwood veneer 1,5
		Oak
		High Performance Masterresist Lacquer
		Protective edge with recycled carton (95% recycled paper)
		Climate protection of PE film
<ul style="list-style-type: none"> Packaging contents 	pack pallet	8 planks = 1,23m ² 88 packs = 107,99m ²
<ul style="list-style-type: none"> Environnemental prog. Warranty 		PEFC for Oak, sapele 15 years domestic use Lifetime for locking system
<ul style="list-style-type: none"> Installation 		Mechanical loc: Bestloc and BestLoc X-TREME no glue, no tools (see the installation instructions available on berryalloc.com)
	DTU 51.11 DTU 51.2	Floating laying (french installation rule) Glued fitting (french installation rule)
<ul style="list-style-type: none"> Underfloor heating 		suitable (see the specific requirements for wood floors above underfloor heating on the web site)

Classification	Norme	Unit	Mesures
<ul style="list-style-type: none"> Abrasion resistance 	CS10 (NF Parquet) EN 13329 (Test S42)	Tour (TT) Tour (TT)	6000-9000 >700
<ul style="list-style-type: none"> Gloss value 		Gloss 60° Gloss 60° Gloss 60°	27 +/- 2 (satin) 15 +/- 2 (patina) 7 +/- 2 (matt)
<ul style="list-style-type: none"> Fire class 	EN 13 501-1	Oak, Maple, Sapelli, Doussie	Dfl-S1
<ul style="list-style-type: none"> Slippery 	XP CEN TS 15676		
<ul style="list-style-type: none"> Adhésion Thermal resistance European class (based on unfinished wood) 	ISO 2409 EN 685	Adhesion coefficient m ² K/W	1 Oak: 0,066 (other speices from 0,062 to 0,067)
<ul style="list-style-type: none"> Loc System Joint strength 		Oak / Beech Jatoba, Can. Maple Kg / m Kg / m	23 31 Long side > 550 Short side > 1 000
<ul style="list-style-type: none"> Marquage CE Formaldehyde emission VOC emission 	EN 14342 EN 717-1 ISO 16 000-9	ug/m ³ ug/m ³	E1 A+

Maintenance

See instructions on berryalloc.com

For commercial use, please take contact with us.

