

Product description

	Unit	
<ul style="list-style-type: none"> Parquet V-Groove Format (L x w x h) 	mm	Single plank on the long sides 1980 x 164 x 13,2
<ul style="list-style-type: none"> Facing thickness genuine hardwood Total thickness Weight 	mm mm kg/m ²	2,5 13,2 11
<ul style="list-style-type: none"> Moisture content (when delivered) Core layer Backing layer Species offered Surface treatment Packaging 	% mm mm	7-10 Brown HDF thickness 9,2 Softwood veneer 1,5 Oak High Performance Masterresist Lacquer Protective edge with recycled carton (95% recycled paper) Climate protection of PE film
<ul style="list-style-type: none"> Packaging contents 	pack pallet	6 planks = 1,948 m ² 50 packs = 97,41m ²
<ul style="list-style-type: none"> Environnemental prog. Warranty 		PEFC for Oak 15 years domestic use Lifetime for locking system
<ul style="list-style-type: none"> Installation 		Mechanical loc: Bestloc and BestLoc X-TREME no glue, no tools (see the installation instructions available on berryalloc.com)
<ul style="list-style-type: none"> Underfloor heating 	DTU 51.11 DTU 51.2	Floating laying (french installation rule) Glued fitting (french installation rule) suitable (see the specific requirements for wood floors above underfloor heating on the web site)

Classification	Norme	Unit	Mesures
<ul style="list-style-type: none"> Abrasion resistance 	CS10 (NF Parquet) EN 13329 (Test S42)	Tour (TT) Tour (TT)	6000-9000 >700
<ul style="list-style-type: none"> Gloss value 		Gloss 60° Gloss 60° Gloss 60°	27 +/- 2 (satin) 15 +/- 2 (patina) 7 +/- 2 (matt)
<ul style="list-style-type: none"> Fire class 	EN 13 501-1	Oak	Dfl-S1
<ul style="list-style-type: none"> Slippery 	XP CEN TS 15676		
<ul style="list-style-type: none"> Adhésion Thermal resistance European class (based on unfinished wood) 	ISO 2409 EN 685	Adhesion coefficient m ² K/W	1 Oak: 0,080
<ul style="list-style-type: none"> Loc System Joint strength 		Oak Kg / m Kg / m	23 Long side > 550 Short side > 1 000
<ul style="list-style-type: none"> Marquage CE Formaldehyde emission VOC emission 	EN 14342 EN 717-1 ISO 16 000-9	ug/m ³ ug/m ³	E1 A+

Maintenance

See instructions on berryalloc.com

For commercial use, please take contact with us.

